

TEST REPORT

No.: GZPH220300166301SC

Date: Mar 15, 2022

Page: 1 of 3



CUSTOMER NAME: GUANGDONG GONGLI BUILDING MATERIALS CO., LTD.

ADDRESS: NO.9-2-1, CENTRAL TECHNOLOGY INDUSTRIAL ZONE C, JIAHE

BEI ROAD, LUBAO TOWN, SANSHUI, FOSHAN

Sample Name : PLASTIC TILE

Manufacturer : GUANGDONG GONGLI BUILDING MATERIALS CO., LTD.

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

Date of Receipt : Mar 07, 2022
Testing Start Date : Mar 07, 2022
Testing End Date : Mar 15, 2022

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to

the sample(s) tested)

Signed for SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch Testing Center

Quincey Lee

Quiney

Authorized signatory





TEST REPORT

No.: GZPH220300166301SC

Date: Mar 15, 2022

Page: 2 of 3

Summary of Results:


No.	Test Item	Test Method	Result	Conclusion
1	Thermal Conductivity	ASTM C518-21	0.091 W/(m·K)	1

Note: Pass : Meet the requirements;

Fail: Does not meet the requirements;

/ : Not Apply to the judgment.

Original Sample Photo(s):





Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printer overleaf, available on request or accessible at https://mem.and-conditions.aspy and, for electronic format documents subject to Terms and Conditions for Electronic Documents at https://mew.sgs.com/en/Terms-and-Conditions.Terms-e-Document.aspy. Attention is drawn to the limits or disability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits or transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing //imspection report & certificate, pelase contact us at telephone; (86-755) 8307 1443.



TEST REPORT

No.: GZPH220300166301SC

Date: Mar 15, 2022

Page: 3 of 3

Test Item: Thermal Conductivity
Test Method: ASTM C518-21

Test Condition:

Specimen: 302mm×301mm×6.6mm, 1pc

Density: about 1928kg/m³
Mean temperature: 31°C

Temperature difference: 10 °C

Lab Environmental Condition: 23±2℃, 50±5%RH

Test Result:

Test Item	Test Result
Thermal Conductivity	0.091 W/(m·K)

Note: The test result can not be compared with other results obtained from different test conditions, and should not be cited to the use condition directly.

Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Thermal Conductivity Tester	HFM 436/3/1E	SJ-65	2021/7/19	2022/7/18

Note: The above test was carried out by SGS-CSTC Standards Technical Services (Shanghai) Co., Ltd. laboratory.

****** End of report******



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at https://mem.and-conditions.aspx and, for electronic format documents subject to Terms and Conditions for Electronic Documents at https://mew.sgs.com/en/Terms-and-Conditions.frems-e-Document.aspx Attention is drawn to the limitation or liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits or transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduce except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or faisification of the content or appearance of this document is unlawful and offenders may be prosecuted to the full liest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

**Attention: To check the authenticity of testing /imspection report & certificate, plear certained for 30 days only.